



MIROSLAV SYVYI¹, PETRO DEMYANCHUK²,
BOHDAN HAVRYSHOK³, BOHDAN ZABLITSKIY⁴

Phosphates of Ukraine as raw materials for the production of mineral fertilizers and ameliorants

Introduction

Ukraine is a consumer of phosphate and complex phosphorite mineral fertilizers, however the extraction of raw materials and production of phosphate fertilizers and ameliorants is done in small amount. At present, Ukraine produces phosphate fertilizers at only two enterprises: Public Joint-Stock Company (PJSC) «Sumykhimprom» and PJSC «Dniprovskiy Plant of Chemical Fertilizer» that has a total production capacity of 1434 thousand tons 100% P₂O₅ in the form of complex mineral fertilizers. PJSC «Crimean TITAN» is located on the territory of the annexed Crimea and is not actually controlled by Ukraine.

✉ Corresponding Author: Bohdan Havryshok; e-mail: gavrishok_b@ukr.net

¹ Ternopil Volodymyr Hnatiuk National Pedagogical University, Ukraine; ORCID iD: 0000-0002-3150-4848; e-mail: syvyjm@ukr.net

² Ternopil Volodymyr Hnatiuk National Pedagogical University, Ukraine; ORCID iD: 0000-0003-4860-7808; e-mail: dempetrom@gmail.com

³ Ternopil Volodymyr Hnatiuk National Pedagogical University, Ukraine; ORCID iD: 0000-0002-8746-956X; e-mail: gavrishok_b@ukr.net

⁴ Ternopil Volodymyr Hnatiuk National Pedagogical University, Ukraine; ORCID iD: 0000-0003-3788-9504; e-mail: zablotskiy@ukr.net



© 2019. The Author(s). This is an open-access article distributed under the terms of the Creative Commons Attribution-ShareAlike International License (CC BY-SA 4.0, <http://creativecommons.org/licenses/by-sa/4.0/>), which permits use, distribution, and reproduction in any medium, provided that the Article is properly cited.

Due to the termination of the supply of Khibiny apatite from the Russian Federation, Ukraine faced the problem of providing mineral fertilizer plants with phosphate raw materials, originally supplied from Syria, which is now at war, and deliveries (mainly phosphorites) were done from North Africa and the Middle East. Meanwhile, by January 1, 2018, 7 deposits of apatites (5 complex ores) with the resources of industrial categories of 71 911 thousand tons of P_2O_5 and 9 deposits of phosphorites (4 complex ores) with industrial resources of more than 11090 thousand tons of P_2O_5 were explored and listed in the State Balance (Korpan et al. 2018a). In 2017, six of them were listed to be mined or to be given a license but in fact, only 650 tons of phosphorite ore or 50 tons of pure P_2O_5 were extracted. Therefore, the actual production of phosphate fertilizers is carried out almost exclusively by means of imported raw materials supplies. Explored complex apatite deposits require a significant investment to start to be developed. Phosphorite concentrates and mineral fertilizers produced from them are of lower quality than those made of apatite and will obviously be consumed only within the country. The use of low-grade phosphate raw materials has, in recent years, generally become a global trend. The mentioned facts explain the importance of the immediate industrial reanimation of the phosphorite deposits as the source of the phosphate raw material industry. Current tasks are to carry out a geological and technological re-estimation of traditional phosphorite ore deposits and an evaluation of the new geological and industrial ones in order to process them into soluble mineral fertilizers. In Ukraine, the quality of the ore from the explored deposits is considered to be low and ores require special processing methods.

The aim of the article is to analyze the existing deposits of phosphate raw materials in Ukraine, to define their ability for industrial use, to suggest ways of their efficient use and expansion of the raw material base for supplying local chemical plants for the production of modern phosphorus and complex mineral fertilizers which would prevent (at least partly) from expensive imported phosphate transportation.

In Ukraine, resources of phosphate raw material are represented mainly by deposits of apatites, phosphorites and glauconites.

1. Apatite raw materials

Four main genetic types are distinguished among the deposits of apatite ores which are the main raw material base for the production of traditional mineral fertilizers (superphosphate, ammophos etc.): magmatic, metamorphic, carbonatite and weathering crust. In Ukraine, all geological and industrial types of deposits are found. Seven deposits of complex apatite-ilmenite ores are listed in the State balance of reserves: Kropyvna, Stremyhorod, Torchyn, Fedorivka (Zhytomyr oblast) and Nosachiv (Cherkasy oblast) (Table 1) where apatite is considered as a supplementary raw material, as well as two deposits of apatite-ilmenite ores – Davydky (Zhytomyr oblast) and Novopoltavka (Zaporizhia oblast), where apatite was defined as the main mineral resource. At present, none of the deposits are being developed.

Table 1. Resource base of apatite ores of Ukraine

Tabela 1. Baza surowcowa rud apatytowych Ukrainy

Oblast	Deposit name	Type of deposit	Type of ore	Mineral resources (A+B+C ₁ +C ₂) thousand tons P ₂ O ₅ thousand tons	Average P ₂ O ₅ content in ore [%]
Cherkasy	Nosachiv	1) magmatic 2) weathering crust of the Gabroids	apatite-ilmenite	359714/43966	No information
Zhytomyr	Stremyhorod		apatite-ilmenite	886344/23688	2.4
	Fedorivka		apatite-ilmenite titanomagnetite,	129776/3919	3.0
	Davydky		apatite-ilmenite	57022/2069 (C ₁ +C ₂)	3.63
	Kropyvna		apatite-ilmenite titanomagnetite,	221730/5419 (C ₁ +C ₂)	2.15 (1.8–2.45)
	Torchyn		apatite-ilmenite	209090/696	0.3
Zaporizhia	Novopoltavka	1) carbonatite 2) weathering crust and carbonatite	apatite-rare-metals	859623/46578	4.9
Total:				2363585/126335	–

The **magmatic type** is represented by deposits in Stremyhorod, Fedorivka, Nosachiv and others are related to Korosten and Korsun-Novomyrhorod pluton of the Ukrainian shield and associated with the formation of gabbro-anorthosites. They contain complex ilmenite-apatite-titanomagnetite ores. In the weathered crust of the Gabroids occur residual and infiltrational type deposits of apatite-ilmenite ores of industrial value. The P₂O₅ content of such ores ranges from 0.01 to 5.8%.

On the basis of *Stremyhorod* apatite-ilmenite deposit located near the Irshansk Mining and Processing Plant, it is possible to establish an enterprise with an annual production of 860 thousand tons of apatite concentrate with a P₂O₅ content of 38%. Ores are easily enriched with the simultaneous release of ilmenite, apatite and titanium-magnetite concentrates of high quality. A special permit for resource use in Stremyhorod deposit, 20 kilometers from the village Irshansk, was obtained by LLC «Valki Ilmenite» in 2012.

The *Nosachiv* deposit of apatite-ilmenite ores of the Korsun-Novomyrhorod pluton was transferred to “Tiofab” Ltd. for exploitation (2007). The deposit has a similar mineral content as the well-known Telnes ilmenite deposit in Norway, Rogaland province (without or with little magnetite). The technological features of the ores from the Nosachiv deposit are similar to the ores of Stremygorod and Fedorivka deposits, but they are considered to be technologically better and easily enriched. The ores can be processed by the technologies used at these two deposits, but fewer operations are required. According to the developed

beneficiation technology, obtaining apatite concentrate containing P_2O_5 of not less than 39% is planned. Apatite concentrate is a substance rich in phosphorus and fully meets the requirements of the European Economic Association concerning the production of phosphate fertilizers. The expected total cost of the ore mining and processing plant for the development of Nosachiv deposit will be (Dubyna 2010a), approximately, about USDUSD 250 million and the period of the plant construction with its full production capacity will be up to 5 years.




Fig. 1. Occurrence of resources of phosphate raw materials in Ukraine

Rys. 1. Występowanie zasobów surowców fosforanowych na Ukrainie

The geological and economic estimation of the Southern part of *Davydky deposit* of ilmenite apatite ores in Narodychiv district of Zhytomyr oblast has revealed the reserves of bedrock ores in the categories C_1+C_2 in the amount of 57022 thousand tons with the average P_2O_5 content of 3.63% and TiO_2 – 5.53% (Table 1). The general off-balance inferred resources of C_2 category are 47 243 thousand tons with an average P_2O_5 content of 1.13% and TiO_2 – 6.31%. According to the technical and economic calculations (Melnyk 2015), the index of cost-effectiveness to the cost price is estimated as 16.4%, the payback period of the primary investments is 9.9 years, the index of profitability is 1,007, the index of the enterprise profitability is 0.274. However, the State Service of Geology and Subsoil of Ukraine has canceled the special permit for a private enterprise “DBR-3” to extract ilmenite-apatite ores from the Southern part of Davydky deposit due to their refusal to pay the state budget for the permit to use the resources. Therefore, now the deposit is expecting its investor.

According to the exploration data of the *Kropyvna deposit* (Merkushyn 2014), which is located in Volodar-Volynskyi district of the Zhytomyr oblast and is related to bedrock-ultrabasic intrusion, two types of ores are distinguished: the weathering crust and bedrock, which, consequently, make up two ore bodies. Mining, engineering, geological, hydrological and hydrogeological conditions of the deposit are favorable for opencast mining. The ore reserves will provide ore for the mining company with a capacity of 12,000 thousand tons per year for a period of 18.4 years. The deposit is completely prepared for industrial mining even in uncertain economic conditions. In 2007 the gas trader «Sirius» received a permit to mine the Kropyvna deposit. The deposit is located fifteen kilometers from the Irshansk Mining and Processing Plant. It claimed the need of USD 2.2 billion investment (Chernovalov 2011). The company promises to invest USD 230–250 million in the mining at the first stage. The money should be spent on building a mining and processing plant with an annual capacity of 12 million tons of ore. The production of titanomagnetite concentrate will make 1.68 million tons of ilmenite concentrate – 0.3 million tons and of apatite concentrate – 0.66 million tons.

In addition to the mentioned above, a number of previously evaluated deposits in the Irshansk mining region within the boundaries of the Ukrainian Shield are defined, particularly deposits in: Vydybor, Paromiv, Yuriv, Slavechne. More than 10 potentially valuable ore occurrences were discovered. The total resources of P_2O_5 in the mining industry are 258 million tons with P_2O_5 content of 3–10% in the ore (Brahin 2000a).

In the Archean plagioclase-pyroxene crystalline shale near the village Tropove of the Mohyliv-Podilskyi district (Vinnytsia oblast), the occurrence of large apatite impregnation has been revealed. A group of steeply falling ore bodies (each of 30–40 m thick) was found in wells with the thickness of 60–300 m. The content of P_2O_5 in the bodies varies from 2.0–4.2%. The total projected resources are estimated at 20 million tons.

The apatite occurrence in the crust of weathering of serpentinites with the apatite content of 20–30 kg/t are found in the Khmilnytsk district of the Vinnytsia oblast.

Carbonatite ores are represented by the deposit in Novopoltavka (Fig. 2) and the ore exposition of Pre-Azov area, Proskuriv and other potentially valuable massifs of Podillia. Particularly, in the Letychiv district of the Khmelnytskyi oblast within the Holoskiv apa-




Fig. 2. Novopoltavka deposit (schematic geological section) (Mychajlov et al. 2007)

1 – loam, clay, sand; 2 – migmatite, gneiss; 3 – weathering crust; 4 – granitoid;
 5–7 – apatite rocks: 5 – carbonate; 6 – albitite; 7 – syenite;
 PR – primary ore, MZ – residual and infiltration type ore, KZ – overburden

Rys. 2. Złoże Novopoltavka (schematyczny przekrój geologiczny)

1 – il, glina, piasek; 2 – migmatyt, gnejs; 3 – zwietrzała skorupa; 4 – granitoid;
 5–7 – skały apatytowe: 5 – węglan; 6 – albit; 7 – sjenit;
 PR – ruda pierwotna, MZ – ruda resztkowa i infiltracyjna, KZ – nadkład

titeous area, the potential exposition of apatite ores with projected resources of 30 million tons of P_2O_5 are identified. The examples of such deposits can be a number of unique apatite deposits in Russia (Khibiny, Kovdor) and Canada (Cargill, Martinson).

In 1990, the feasibility study of the construction of an underground mine and a concentrating mill near the *Novopoltavka deposit* of apatite-rare-metals ores was carried out. The practically wasteless apatite ores processing technology enables up to 1650 thousand tons of apatite concentrate with the content of anhydride of phosphoric acid of 38% per year to be received. The development of the Novopoltavka deposit alone can fully supply Ukraine with apatite and such rare metals as: Nb, Ta, Ce, La, Nd, Sr for the next 25–50 years. The concentration of rare metals in rare earth apatites can reach 11% of TR_2O_3 . In addition, fluorine can simultaneously be extracted from the apatite which contains a high content of this mineral (up to 3,3% F). It is also possible to obtain 1.45% of rare earth elements in the ore enrichment process, which significantly increases the profitability of the development of the deposit. The rare earths extraction from apatite can completely cover the costs of the deposit development (Dubyna 2010b). The “Volyn Mining and Chemical Company” Closed Joint-Stock Company investor is currently obtaining the approval and carrying out the examination for further exploitation of the deposit.

2. Phosphorite raw materials

In Ukraine, the deposits of ores that contain phosphorite are widespread within the Volyn-Podillia plate, the Dnieper-Donets rift, the north-eastern slope of the Ukrainian shield, the southwestern slope of the Voronezh crystalline massif and the Indo-Kuban trough which are connected with the deposits of Upper Precambrian (Vendian), Cretaceous, Paleogene and Neogene ages. Phosphorites are found among the layers of marls, argillites, quartz-glaucconite sands, less often sandstones and limestones in the form of small nodules, pebbles. Meanwhile, the thickness of deposits varies from 0.5 to 10–15.0 m, and the content of P_2O_5 in the ore can be from 4.0 to 50.0%.

According to the mode of occurrence of the phosphate component, Ukrainian phosphorites are divided into nodular, granular, mixed-type and brown iron ore phosphorite. The first three types are the most widespread and industrially important.

Nodular phosphorites are formed of separate concretions of different sizes (1–2 to 10–15 cm) included in the rock (clay, sand, chalk, etc.) and unevenly spread in it. They are found on the territory of Middle Dniester in the form of bedrock layers and in the Volyn, Polissya, Dnieper-Donets rift in the form of redeposits (Senkovskij et al. 1989a).

Three phosphorite-bearing basins are distinguished within the southwestern part of the Eastern European Platform: Podillia Vendian, Volyn-Podillia Cretaceous and Polissia Paleogene (Senkovskij et al. 1989b), another basin of Cretaceous Age – Dnieper-Donetsk – is identified on the left bank of the Dnieper river.

The **Podillia Vendian basin** covers the area of development of Vendian Kalus bed within the southwestern slope of the Ukrainian shield. Phosphorite content is predominantly found among the deposits of the Nahirianka Vendian formation. It is also occasionally found in the earlier deposits of this system.

The areas of occurrence of Kalus beds (mynkivets horizon) are located in the Middle Dniester, in the Dniester valley and the Dniester's left tributaries: the Zhvan, Kalus, Ushytisia, and wells are also found on the basins of the Southern Bug and Horyn. The productive horizon with the thickness of 5–25 m is composed of a monolith of dark gray or gray-green thinly layered shale argillites with interlayers of the siltstones. Phosphorites are represented by concretions of 2–25 cm in diameter. The content of P_2O_5 in bedrock phosphorites of the Kalus beds is 30–38%, consequently they can be considered high-quality raw materials to produce phosphate fertilizers – superphosphate, phosphorous flour etc.

During Cretaceous (Albian) transgression, Vendian phosphorite deposits were affected by intensive erosion and subsequent redeposition of phosphorites in shallow basins extending along the flooded southwestern part of the Ukrainian shield. Thus, the redeposited concretionary phosphorites, which were formed in this way make up the basal layer of the Mid-Upper Albian and overlying Lower Cenomanian deposits. The latter one along with the bedrock Cretaceous phosphorite form the **Cretaceous Volyn Podillia Basin** (Senkovskij et al. 1989c).

Phosphorite occurrence of the *Middle Albian* age described by Y. Senkovsky and others (Senkovskij et al. 1989d) is found in the Borshchiv district of Ternopil oblast in the

Hudykivtsi and Pylypche villages. Productive deposits are formed by shellfish and sandy phosphorites and occasionally by pellets (round objects of 0.06–2 mm), phosphoritized wood and remnants of elasmobranchs (teeth). They form rich clusters 0.3–0.5 m thick with the phosphorite content of 40–50%. No special geological exploration on revealing the phosphorite content in the Middle Albian has been carried out until now.

In the Upper Albian horizon, phosphorites of two genetic types are present: redeposited concretions of the Vendian age and bedrock sandy nodule phosphorites.

Redeposited Vendian concretion phosphorites lie among the coarse-grained rocks (conglomerates) of Albian age and are found near the following villages: Liadova, Bernashivka, Hlybivka and others (Khmelnyskyi oblast), where they constitute a productive horizon with a thickness of 0.2–1.0 m.

According to various researchers, the resources of phosphorite concretion do not exceed 300–500 thousand tons, and the deposit productivity can be no more than 300 kg/m² (while earlier the productivity of these horizons was 1,000–1,800 kg/m²). However, Y. Senkovsky and others (Senkovskij et al. 1989e) consider the territory of the plateaus between the left-hand tributaries of the Dniester to be potentially valuable for the discovery of new industrial concentrations of this type of phosphorites. However, the possibility of deposit development is problematic because the productive layer lies at a depth of 100 m and can only be developed by underground mining.

Upper Albian bedrock phosphorites lie among the quartz-glaucanite sands and have a good outcrop in Mohyliv Podnistrovia (Dzhyhivka, Naslavcha and others).

Next to the Zhvan village in Murovani Kurylivtsi district, a mixed-type *Cenomanian* phosphorite deposit (Zhvan deposit) was discovered in 1954 (Fig. 3). The deposit was predominantly represented by nodule and granular phosphorites of 0.1–0.5 mm – 2–5 cm and




Fig. 3. Zhvan deposit (schematic geological section) (Mychajlov et al. 2007)

- 1 – loam, clay, sand; 2 – clay, limestone, sand; 3 – chalk, marl; 4 – argillites, siltstone, sandstone;
 5 – quartz-glaucanite sandstone with pebbles of phosphorites;
 Q – Quaternary, N – Neogene, K – Cretaceous, PR – Precambrian

Rys. 3. Złoże Zhvan (schematyczny przekrój geologiczny)

- 1 – il, glina, piasek; 2 – glina, wapień, piasek; 3 – kreda, margiel; 4 – argillity, kamień ilasty, piaskowiec;
 5 – piaskowiec kwarcowo-glaukonitowy z kamykami fosforytów;
 Q – czwartorzęd, N – neogen, K – kreda, PR – prekambr

phosphorite-bearing glauconite sand and additionally by redeposited spherical concretions and their parts (Table 2). The phosphorite horizon with the thickness of 8/10–20/30 m lies at a depth of 70–100 m and reaches the surface only on the slopes of the river valleys. The thickness of the ore layer is 0.9–1.5 m. Only the reserves of the Northern section are rated C₁ category and are estimated at 752 thousand tons calculating as an enriched concentrate with a P₂O₅ content of 16%. The thickness of the ore layer is 450–470 kg of concentrate per 1 m².

The technical and economic calculations concerning the deposit done in the 1960's and 1990's were based exclusively on the data of this section, though there are ore outcrops of significantly higher rates. A detailed study (exploration is currently being conducted in the deposit in the Mohyliv-Podillia and Murovani Kurylivtsi districts) may enable the areas with ore resources of 2–3 million tons to be defined (Korpan et al. 2018b).

Phosphorite and glauconite ores with a similar composition to Zhvan and with favorable conditions for underground mining are also found near the villages of Dzhyhivka, Rusava, and Porogiv (Yampil district). The deposits require further exploration (Syvyj 2004a).

In general, 8 deposits and almost 90 phosphorite occurrences were detected on a narrow area 8–18 km from the city of Yampil, Vinnytsia region, to the city of Khmelnytskyi. They are found mainly in Cretaceous sediments and are represented by nodular phosphorites of the plastogenic and organogenic structure, as well as shellfish, spongiform and phytomorphic types. In addition, there are lenses and thin layers of phosphorites containing P₂O₅ of 10–15% (Weshyckyj 2004a).

The preliminary exploration of the areas in Zozulyntsi in Krasyliv district and the Fashchiivka in Derazhnia district of the Khmelnytskyi oblast (Korpan et al. 2018c) has been completed and the resources of 93.2 million tons of ore have been found.

The Lower Cenoman phosphorite-bearing horizon appears at the ground surface between the Studenytsia and Kalius rivers and nearby areas. Here, the productive horizon is represented by quartz-glauconite and glauconite sands with a thickness of 3–6.5 m, with nodules of sandy phosphorites and concretions of brown iron ore. The content of phosphorites in sand reaches 15% and more.

In Volyn-Podillia plate occur also deposits of granular phosphorites which are the potential raw material base for phosphate fertilizer production. These are the Cenomanian phosphorites which are glauconite-phosphate-quartz sandstones on carbonate chalk cement. There are a varied types of carbonate replacement by phosphate substance (with the content of P₂O₅ from 6 to 38%) with an easily recoverable form of phosphorus oxide. The mineralogical composition of granular is: phosphorite and glauconite, phosphates, quartz, feldspars, calcite, hydromicans.

The deposits of granular phosphorites of Volyn-Podillia phosphorite-bearing basin are found within the Manevychi-Klevan and Zdolbuniv-Ternopil potential areas. The main useful mineral (phosphorite agricultural ore) is considered to be glauconite-phosphorite-quartz sand, inoceramus-glauconite-phosphorite-quartz sandstones and glauconite-phosphorite-quartz accompanying them glauconite-phosphorite sandy limestones are regarded as

Table 2. Phosphorite resource base in Ukraine

Tabela 2. Baza zasobów fosforytu na Ukrainie

Deposit age	Deposit type	Mining ore type	Deposits, potential areas	Mineral resources, phosphorite ore, P ₂ O ₅ , [thousand tons]		Inferred resources P ₂ O ₅ , [thousand tons]	Content P ₂ O ₅ [%]
				B+C ₁	C ₂	P ₁	
Podillia Vendian basin	bedrock	nodular	No explored deposits	–	–	–	30–38
Cretaceous Volyn Podillia basin	mixed type	mixed type	Zhvan deposit, north part	10057/752	–	–	3–5
			Zozulyntsi	–	93.2	–	0.7–9.7
	redeposited	mixed type	Fashchivka	–	–	–	–
			Nezvysko	14700/370	4035/320	–	1.2–12.6
	granular	granular	Myliatyn	4000/213	3583.4/247	100	6–7
			Zdolbuniv	–	–	7100	0.3–8.5
			Kopytkove	–	–	–	5.2
			Mateiky	–	–	95.6	5.9
			Bilohiria	152000	–	–	1.0–10.6
			Karpivka	556.3/32.6	1291.5/72.6	–	5.7
Cretaceous Dnieper-Donetsk basin	bedrock	bedrock	Osykove	11300/593	–	–	5.26
			Ray-Olexandrivka Zvanivka	–	–	2500	–
			Viazovatyi Yar	40.6/3.66	23.2/2.3	–	–
	nodular	nodular	Synychno-Yaremovske Mala Komyshevaha	–	–	–	13.1 до 9.3
			Krolevets	7885/1103	–	–	13–15
			Bantyshivka area Dobropillia area	–	–	2700 1000	5.0–8.14 4.1
Paleogene deposits	bedrock	nodular	Ratne deposit Postupelska area	– 3500/340	–	8200	6.7 9–16
	redeposited		–	–	–	–	
Neogene deposits	bedrock	granular glauconite	Kyz-Aulske Komyshevaha Eltyhen-Ortelske	300004/6663	–	–	2.17 2.19 2.58
Man-made deposits	–	granular glauconite	Verbka	250/26.7	–	–	–

supplementary minerals (agricultural ore for soil deacidification with simultaneous phosphorus enrichment). The total thickness of deposits is up to 6 m with 250 m of overburden and up to 15% of the P_2O_5 content. In granular deposits the phosphoritized molluscs' shells is the prevailing mode of phosphate occurrence. Prospective resources (P_2) of granular phosphorites of the mentioned above areas are estimated respectively 173.6 million tons (Korpan et al. 2018d).

Within the Zdolbuniv-Ternopil area, *Myliatyn deposit* (Ostroh district) is of considerable interest and is listed in the State balance of mineral reserves (Table 2). Genetically granular phosphorites of this deposit occur within marine terrigenous-carbonate deposits of the Cenomanian stage of the upper Cretaceous. The deposit can be openpit mined (the overburden thickness is not more than 12 m). It contains 247 thousand tons, inferred resources are another 100 thousand tons with 6–7% of P_2O_5 content. The experimental pilot and industrial development of the deposit is carried out by the Western Ukrainian mining enterprise. Due to the complicated mining and geological conditions of the phosphorite occurrence, specifically, high water content in the deposit forming rocks and their location on private arable lands and under built-up areas, scientists of the National University of Water and Environmental Engineering (Rivne) instead of surface mining suggested the method of well hydraulic mining, which allows the cost of exploitation to be reduced by 2–3 times along with minimizing the detrimental effects on the environment (Bobliakh 2013).

A deposit of granular phosphorites *Mateiky* is present in the north-eastern part of Volyn oblast, on the territory of Manevychi district. Here the productive horizon is represented by fine-grained glauconite-phosphate-silica sandstone with carbonate cement. The total projected stock is 95.6 million tons of ore, or 5.9 million tons of P_2O_5 with its content of 1.1–9.5% (Weshyckyj 2004b).

The Upper Cenomanian phosphorite-bearing horizon in Mohyliv-Podilskyi, in Podnistrovia is defined to be connected with so-called inocerum limestone. Phosphorites in limestones occur in the form of nodule and bunchy clusters of phosphate substance (nodule sandy phosphorites), phosphatized organic fossils (sponges, shells and coprolitic phosphates, pellets), in the form of phosphate substance thinly spread in a carbonate mass that appears to impregnate the rock (phosphate limestone). The thickness of the phosphorite horizon varies from 0.2 to 3 m. The accumulation of the phosphatized fauna of the Upper Cenomanian is found near Liadova, Mohyliv-Podilskyi, Buchach and others. No exploration works on the mentioned phosphorite-bearing areas have been done yet.

Projected phosphate chalk (chalk limestone) resources in Vinnytsia Podnistrovia make up (Ukrainets 2006a): in Mohyliv-Podilskyi district – 15.9 million ton (Mohyliv-Podilskyi, Ozaryntsi and Sloboda-Yaryshkivska deposits), in Murovani Kurylivtsi district – 60 million ton (Bakhtyn and Kryvi Hyzhyntsi area).

The phosphate chalk deposits of the region occur in favorable conditions. The thickness of the overburden rock is 3.5–4.0 m, on average. In some places, they are even developed together with other chalk rocks for building needs. The possibilities of their usage are described below.

The deposit in *Osykove*, Starobeshiv district, Donetsk oblast (Table 2) belongs to **Cretaceous Dnieper-Donetsk basin** connected with the Kryva Luka Upper Cretaceous formation. The deposit is represented by quartz-glaucconite sand overlapped by slightly phosphatous Neogene sands. The content of P_2O_5 ranges from 3 to 14% (the average is 5.2%). Stocks, calculated according to industrial categories, make up 593 thousand tons of phosphorus anhydride. The thickness of the deposit varies from 1.0 to 16.1 m, the average is 5.83 m. The average thickness of overburden rocks is 29.3 m. The South Osykove site is located in the southwestern part of the Osykove deposit where the average thickness of the overburden rocks is not more than 15 m. The area is being prepared as a local phosphate raw material base. The capacity of the occurrence ranges from 4.4 to 15 m (the average is 8.01 m) (Brahin 2000b).

The “Donetskgeologija” State Regional Geological Enterprise began a phosphorite search and evaluation within the limits of the trough in Kryva Luka where two areas (Zvanivka and Ray-Oleksandrivka) with phosphorite rocks of Cretaceous age, have been defined. They lie under the Quaternary sediments, the thickness of which reaches 11.0 m, and in the gully they may appear on the surface. A phosphorite stratum occurs at an angle of 30° and can be traced to the depth of 70.0 m (more than 100.0 m in some areas). The total projected resources are estimated at 2.5 million tons of P_2O_5 (Korpan et al. 2018e).

Well-known phosphorite-bearing regions of the Upper Cretaceous age include the Iziium-Donbas area located within the Kharkiv, Lugansk and Donetsk oblasts, where the deposits of Kremenets, Kryva Luka, Lysychansk, Mala Komyshuvaha, Bakhmutske, Synychno-Yaremyvske are situated. Iziium phosphorites are mineralogically and petrographically similar to phosphorites of the Krolevets deposit (Chernihiv oblast) as concretions are mostly sandy with P_2O_5 content of 14–19%. The recently established “Iziium Phosphorites” Private Limited Company began preparations for the development of the deposits of the area. It is going to process raw materials for phosphorite flour (Korpan et al. 2018f).

Two potential phosphorite-bearing areas of the *Paleogene age* are distinguished on the territory of the Donetsk oblast (Table 2).

Bantyshivka area is located in Sloviansk district. The sands of the middle-upper Eocene are found to be productive here. Three horizons with nodule phosphorite are distinguished. The *Dobropillia* area is located in the same district and is also connected with Eocene deposits, represented by glauconite-quartz sand with phosphorite nodules.

In Volyn oblast, *Ratne deposit* of nodular phosphorites, redeposited from the Eocene sediments, was explored. The total projected resources are 121.6 million tons of ore, or 8.2 million tons of P_2O_5 with phosphorus anhydride content of 6.7 percent. The Postupel area where the detailed exploration (340 thousand tons of P_2O_5) was realized, has been prepared for exploitation. Nodule processing can be done in 2 possible ways:

- ◆ nodular grinding and obtaining phosphorite flour with a P_2O_5 content of 14.5% from 91.4 thousand tons directly in the quarry;
- ◆ 90.4 thousand ton of industrial nodules with the P_2O_5 content of 14.5% are sent to beneficiation plants.

The “Volyn mining-chemical company” Closed JSC received special permission (2009) for the industrial development of the field. The estimated capacity of the enterprise is 560 thousand tons of phosphorite flour per year (IPU 2019).

In addition to the Ratne deposit, seven promising Paleogene phosphorite areas (**Polissia basin**) are found: Polissia, Stakhoshynska, Pivnevska, Taniushivska, Novoburlutska, Bantyshevskaya and Zalymanivska with a total area of 4.6 thousand square km and an estimated resources of 335 million tons of P_2O_5 . The deposit parts with a thickness of more than 0.3 m and P_2O_5 content of 5% or more are considered to be potentially valuable areas (Astrelina et al. 2011).

The Kerch Peninsula in the Crimea is known for phosphorus-containing iron ores of the Kerch basin connected with Cimmerian deposits. The eleven deposits among which Eltyhen-Ortelske, Komysh-Burunske and Kyz-Aulske have been developed to different degrees. The total resources of iron ores and of phosphorus anhydride are presented in Table 2. The phosphorous slag produced in the process of iron ore melting (215 thousand tons/year with P_2O_5 content of 11,2% (Brahin 2000c) was previously used as a fertilizer in the western areas of Ukraine on acid soils. Now the mining of these deposits are suspended.

A new mineral type of phosphate raw material has recently been discovered in Ukraine – **Crandallite** (Stylsko, Southern Donbass), though deposits of aluminosilicates have long been known in some countries (USA, Senegal, Russia, Kazakhstan, etc.). Crandallite mineralization in Stylsko is similar to some foreign industrial types of such ores (e.g. the Crandallite ores of Thiès deposit in Senegal contain 29% of P_2O_5). Crandallite is a complex raw material of aluminum and phosphorus, while crandallite ores can be converted into pure aluminum oxide and normal superphosphate (Rudko and Ozerko 2016).

The man-made phosphorite-glaucinite deposit in Verbka (Khmelnitskyi oblast) is also listed in the State Balance. Stocks of phosphorite-glaucinite ore and P_2O_5 are announced as having an uncertain industrial value by the State Service for Geology and the Subsoil of Ukraine (Table 2).

3. Utilization of phosphorites in agriculture

According to the State Institution «Soil Protection Institute of Ukraine» (SPIU 2018), in 2018 189,200 tons of phosphorus (23 kg/ha of sowing area) were ordered by the agricultural enterprises for summer-autumn agricultural work. Ukrainian deposits can only partly supply the necessary amount of phosphate fertilizers. According to the geological and economic estimation, the most potentially valuable for development are considered to be complex apatite ores of the gabbro-anorthosite formations of the Korosten pluton (Stremyhorod, Fedorivka etc.), the formation of ultramafic alkaline rocks and carbonatites (in Novopoltavka). The similar deposits are exploited in Russia, South Africa, Norway. Apatite concentrates are characterized by high content of P_2O_5 , being ecologically clean, they are suitable for processing without significant technological changes at the existing chemical plants of Ukraine

(Shepel 2007). On the other hand, complex apatite deposits explored in Ukraine require a considerable investment in order to begin their development. An alternative way can be the development of numerous explored phosphorite deposits, the raw materials of which are of lower quality and may be used inside the country. Below is a brief overview of the possibilities to use such raw materials.

For example, the calculations done for Zhvan mixed type deposit (Vinnytsia oblast) show that the processing of 14–16% ore concentrate from the deposit into superphosphate is unprofitable. However, phosphorite flour from concentrate or even from unenriched ore can be used directly for acid Podillia soils and can be as efficient as superphosphate. This fact was confirmed by the research on such agricultural crops as sugar beet, potatoes, winter wheat, oats, buckwheat, corn, and others. The flour from Zhvan ore, except for phosphorites, contains 30–40% of glauconite rich in potassium, therefore, the fertilizer can contain both phosphorus and potassium. Glauconite also contributes to the intensive development of bacteria producing nitrogen and enriching soil with nitrogen. It is also calculated (Ukrainets 2006a) that if that ore is used for the production of phosphorite flour, a high rate of return (more than 30%) and a short pay-back period (about 3 years) can be reached. At the same time, the capacity of the future plant is expected to be 150 thousand tons of phosphorite flour per year.

On the deposit, organizing a small experimental and industrial enterprise for the production of phosphorite and glauconite flour from the richest types of ores without their additional beneficiation is recommended. The fact is that during the exploration of the deposit, definite areas with relatively rich ores (6–9% P_2O_5) with the considerable thickness of the productive layer (1–1.5 m) in favorable conditions for extraction were discovered. Flour made of such ores has successfully proved itself in the fields. The development of the deposit can be done only by the adits, though (Syvyj 2004b; Ukrainets 2006b).

The use of local phosphorites and their influence on the crops yield was studied by the Polissia branch of National Scientific Center «Institute for Soil Science and Agrochemistry Research named after O.N. Sokolovsky» (Gavrilyuk 2006a). The conclusions are the following:

- ◆ granular and nodule phosphorites are valuable phosphate-limestone natural agricultural ores, the use of which enables a considerable influence on the soil fertility, crop yield and quality of agricultural products. They are considered to be ecologically clean raw material used for the production of complex fertilizers;
- ◆ the use of phosphorites as phosphate fertilizers on Alfisols helps to stabilize the balance between acid and base in soil solution during crop rotations (potato, barley, spring clover). Depending on the norm, their usage changes the soil solution by making it more basic by 0.3–0.6 points;
- ◆ a comparative evaluation of the basic agrochemical properties of granular and nodule phosphorites indicates that their impact on the soil bio-productivity in the crop rotation zone is more effective than the one done by usual phosphate fertilizers (superphosphate, ammophos);

- ◆ the highest potato yield is directly gained with the use of granular phosphorites with double norm of P_{120} . It helps to increase the harvest of spring barley by 82–95% according to all norms, and green mass of the clover by 4–10% according to absolute control, and by 9–16% and 6–12% according to the standard variant. The direct action of nodule phosphorites increases potato productivity by 42–67%. After nodule phosphorites usage, the yield of spring barley grows by 71–95% and the yield of the green mass of red clover rises by 5–9% according to the control and by 2–16% and 2–12% respectively according to the standard variant;
- ◆ the use of phosphorites on the drained peat soils leads to increase in crop yield comparing with the non-fertilized variant: perennial grass – 33.4 t/ha, corn for green weight – 14.6 t/ha, fodder beet – 15.6 t/ha which is almost as efficient as the use of superphosphate (Lyko and Kolesnyk 2008);
- ◆ granular and nodule phosphorites do not cause an accumulation of heavy metals in the soil, and the amount of nitrates in agricultural products is within the limits of permitted concentration. Local phosphorites contributed to a decrease in the accumulation of radiocaesium in the green mass of perennial grasses by 1.57–1.63 times (Gavrilyuk 2006b).

The experience of experimental and industrial development of granular phosphorite deposit in Karpivka, Donetsk oblast, done by joint-stock company “Agrofos” may be useful while preparing for the development of granular phosphorite deposits in Podillia.

The deposit includes phosphorite-glaucinite-quartz sand and sandstone of Cenomanian age with an average P_2O_5 ore content of 5.86%. The technology of ore beneficiation was elaborated by the Ukrainian State Institute of Mineral Reserves. The development of the deposit began in 1999 by Amvrosiivka Mineral Fertilizers Factory, and during 1999–2001, 20 thousand tons of ore was extracted and enriched, and 7 thousand tons of phosphorite-glaucinite concentrate was obtained. The work of the beneficiation factory proved the necessity to improve the technology of raw material beneficiation (the planned parameters of the concentrate were not achieved). Examining the concentrate revealed that its quality predominates over the granular superphosphate for all soil-climatic zones on condition that it is introduced in relevant doses for the digestible P_2O_5 . The necessity of fine grinding of the phosphate product was not confirmed, therefore, agricultural enterprises successfully used phosphorite-glaucinite concentrate in its natural form (0.25 mm) (Brahin 2003a).

On the other hand, the state does not provide orders for phosphate fertilizers therefore their sales had to be done by direct contracts with agricultural consumers. However it was complicated in those conditions because the customers usually did not have cash. These and some other circumstances caused difficulties in selling products. The factory found the solution in improving the quality of the concentrate by means of the formation of composite mixtures with richer nodule phosphorites, further improvement of the technology of ore beneficiation, increasing the factory capacity which would lead to lowering the selling price and finally, advertising the products (agrofoska) on the internal market. An important

condition for the efficient functioning of such mining enterprises is the conclusion of future contracts for the product supply to consumers (Brahin 2003b).

Evaluation of phosphorite ores for chemical processing can consider the following possibilities (Nepryakhin 2015):

- a) joint processing of apatite and low quality phosphorite raw materials in order to obtain average indicators;
- b) beneficiation of phosphorite ores in order to produce phosphorite concentrates for further standard chemical processing;
- c) application of innovative technologies of beneficiation and chemical processing of phosphorite raw materials to define certain conditions of raw materials.

Actually, the second direction of technological evaluation with obtaining phosphorite concentrate for chemical processing appears the most efficient in the short term. Granular phosphorites turn out to have the best prospects for standard processing among the traditional and new geological and industrial types of phosphorite ores.

The analysis of the use of traditional phosphate mineral fertilizers shows, however, that their efficiency is low due to the fact that plants consume only small amount of phosphorus, but acidic technology requires the maximum high content of P_2O_5 using only rich ores and high quality reagents. In order to solve these problems, according to (VVRU 2011a), implementing the method of the phosphorus mineral fertilizers production (containing calcium, magnesium and silicon), which excludes the use of sulfuric acid and implies the formation of gypsum as a waste product from phosphorus renovation by heating it to the temperatures of 800–1200° C directly from phosphorite ores is proposed. The complex processing of phosphorus raw materials appears to be highly environmentally effective and industrially productive with phosphates that are insoluble in water as its result. This approach enables the industrial development of numerous small phosphorite deposits with small initial capital and thus attracting a larger circle of investors to be started (VVRU 2011b).

Chalk-phosphorite limestones, studied at the exploration stage in Khmelnytskyi and Vinnytsya Podnistrovia, in particular in Murovani Kurylivtsi and Mohyliv-Podilskyi districts, can be considered as powerful complex ameliorants. The content of P_2O_5 ranges from 2 to 5%, and the content of $CaCO_3$ is 76–85%. Such ores do not require enrichment or chemical processing, since a mixture of two essential components, phosphorite and limestone flour, required for the vast majority of local soils are produced during grinding process. The phosphorite component of such flour is marked by a very high solubility degree as the content of the citrate-soluble form of P_2O_5 is more than 55–60% which is 1.5–2 times higher than in phosphorites imported to Ukraine from the Russian Federation which used to import the flour to Ukraine. Limestone component also works more efficiently than the one from dense limestone flour which is produced in the Vinnytsya oblast. The balance between the content of P_2O_5 and $CaCO_3$ in chalk limestones varies according to the local soil needs in these components (Syvyj 2004c; Ukrainets 2006c).

Field studies of the Sugar Beet Institute of the National Academy of Agricultural Sciences of Ukraine confirmed (Ukrainets 2006d), that phosphorite-chalk flour, obtained by

grinding phosphate chalk limestone from one of Vinnytsia deposits, has the same efficient effect on the sugar beet yields and sugar content while being applied once as the total use of artificial phosphorus fertilizers (superphosphate or ammophos and traditional ameliorants such as limestone flour). The tests were carried out on typical Vinnytsia soils such as greyzems (sierzems) and chernozems.

The research also proves the chalk-phosphate flour to be efficient to be used for field beets, winter wheat, barley, rye, potatoes, perennial grasses. Practically all experiments that studied aspects of product quality indicate their improvement, sometimes quite a significant one. For example, the content of starch and vitamin C in potatoes grown using such flour is higher by 22 and 20%, respectively, and the content of nitrates is 1.5 times lower than in the potatoes grown using superphosphate.

The processing chalk rocks into flour is less work- and energy-consuming than dealing with significantly stronger limestones. The cost price per ton of phosphorite-chalk flour ranges from USD 2–3 to USD 5–7 (Ukrainets 2006e) depending on the conditions of raw materials extraction. The cost of 1 ton of phosphorite flour containing P_2O_5 of 30% reaches USD 200 in Ukraine now.

The process of production and use of phosphorite-chalk flour is quite environmentally-friendly, because it does not involve the chemical or thermal processing of raw materials. Phosphorite flour, unlike chemical fertilizers, is practically unwashable from the soil and does not pollute the environment. The European Union and the Russian Federation have the experience of using this type of flour. Defining the area of phosphate-carbonate ores of the Upper Cenomanian and their P_2O_5 content requires further systematic research, especially in potential areas of Mohyliv Podnistrovia (Syvyj 2004d).

Conclusions

1. The chemical plants of Ukraine which specialize in the production of phosphate fertilizers use exclusively imported phosphorite raw materials, mainly from the countries of North Africa and the Middle East. Meanwhile, 7 deposits of complex apatite ores and 9 deposits of phosphorite ores have been explored, listed in the State Balance and prepared for experimental and industrial exploitation. Currently, only one phosphorite deposit is being developed to a small extent, other deposits are not mined.
2. Apatite ores are represented by bedrock apatite, apatite-ilmenite, rare-metal-apatite, crust of weathering of serpentinite deposits; phosphorite ores are: nodular, granular phosphorites, phosphorite-glaucinite and phosphorite-iron ores. At the same time, the total resources of industrial categories only constitute more than 71 million tons of apatite and more than 11 million tons of phosphorite ores calculated at 100% of P_2O_5 . The given figures prove the ability to supply raw material to Ukrainian chemical plants to their full productive capacity for 57 years and enable, at least partially, to reduce the amount of expensive imports of phosphorite raw materials.

3. The ore of Ukrainian apatite-containing deposits is characterized by a relatively low content of the useful component and requires special beneficiation methods. Thoroughly explored apatite-containing bedrock gabbro-anorthosite deposits of Korosten pluton (Stremyhorod, Fedorivka, Nosachiv deposits, as well as carbonatite ores of Novopoltavka deposit) can be primarily recommended for exploitation. All those deposits are complex, therefore they require the construction of enrichment plants, focused primarily on the production of ilmenite or rare earths concentrate, apatite concentrates are considered to be a supplementary useful component. The investors for the exploration have been found, however, this expensive procedure and it is currently being slowed down due to unfavorable investment conditions in the country.
4. The alternative to the use of expensive apatite concentrates may be deposits of local phosphorites with low content of P_2O_5 , explored on Volyn Podillia plate and Dnieper-Donets Rift (Zhvan, Myliatyn, Mateiky, Ratne, Osykove, Karpivka and other deposits). With the content of phosphorus up to 30%, they can be used directly as fertilizers. Soluble forms of phosphate fertilizers are produced from highly concentrated phosphorite flour. Phosphorite fertilizer can be used to change the soil where the most sensitive to fertilizers plants (berry bushes, perennial grass, sugar beet, potatoes, etc.) grow. Other crops use its post-effect which makes it possible to quickly reach the appropriate level of soil phosphorus. Soil phosphorization is equivalent by its efficiency to other methods of applying phosphate fertilizers. More over, so-called granular phosphorite ores of Ukraine are considered to have various agricultural effect as a result of the connection with glauconite, carbonates and microelements and are considered to be the most ecologically-friendly fertilizers in the world due to their reduction of the content of nitrates in soils, etc. They have already started to be developed in Volyn and should form the main phosphorus raw material base for Ukrainian chemical enterprises. Further studies are required to accurately assess the quality of ores and reserves of phosphate-carbonate ores of the Upper Cenomanian of Mohyliv Podnistrovia, granular phosphorites of Volyn-Podillia basin, phosphorite deposits within Kryva Luka trough and others.
5. Phosphate carbonate ores (phosphate chalk) of Upper Cenomanian of Mohyliv Podnistrovia needs further studies in order to properly estimate the quality of ores and reserves, as the ores can be used without expensive processing and be produced into phosphate chalk flour while grinding, which significantly increases the yield of a variety of crops according to previous research.

REFERENCES

- Astrelin et al. 2011 – Astrelin, I., Towasznianskyj L., Loboiko O. and Hryn H. 2011. Technology of phosphorus fertilizers, acids and salts (*Tekhnolohiya fosfornykh dobryv, kyslot ta soley*). Kharkiv: NTU «KhPI», 151 pp. (in Ukrainian).
- Bobliakh, S. 2013. Method of hydraulic borehole mining of granular phosphorite (*Sposib sverdlivnynoho hidrovyy dobytku zernistykh fosforytiv*). *Visnyk Natsional'noho universytetu vodnoho hospodarstva ta pryrodokorystuvannya*, pp. 149–154 (in Ukrainian).
- Brahin et al. 2003 – Brahin, D., Gavrilenko, V. and Bragin, Yu. 2003. Experience in industrial testing Karpovsky deposits of granular phosphorite (*Opyt promyshlennoy obrabotki Karpovskogo mestorozhdeniya zernistykh fosforitov*). *Mineral'ni resursy Ukrayiny* 4, pp. 46–47 (in Russian).
- Brahin, J. 2000. Granular phosphorites of Ukraine (*Zernistyye fosfority Ukrayiny*). Simferopol: Tavria WPP, 73 pp. (in Russian).
- Chernovalov, A. 2011. «Sirius» star plans (*U «Cirusa» zvezdnyye plany*). *Kommersant Ukrayiny* 40, pp. 7 (in Russian).
- Dubyna, O. 2010. Prospects of development of magmatic apatite deposits in Ukraine (*Perspektyvy osvoyennya mahmatychnykh rodovyshch apatyty v Ukrayini*). *Svitohlad* 6, pp. 33–37 (in Ukrainian).
- Gavrilyuk, V. 2006. Agricultural chemistry estimation of phosphor bearing of agroores Western region of Ukraine (on the example of local granular and concretionary phosphorites) (*Ahrokhimichna otsinka fosforytonosnykh ahrorud Zakhidnoho rehionu Ukrayiny (na prykladi mistsevykh zernistykh ta zhovnovykh fosforytiv)*). *Avtoref. dys. kandydat sil'skohospodars'kykh nauk*. Kharkiv, 20 pp. (in Ukrainian).
- IPU (Investment projects of Ukraine. Volyn region) 2019. (*Investytsiyni proekty Ukrayiny. Volyn'ska oblast'*). [Online] <http://investproekt.narod.ru/vol.htm> [Accessed: 2019-03-9] (in Ukrainian).
- Korpan et al. 2018 – Korpan, N., Polunina, H. and Bashkirova H. 2018. Mineral resources of Ukraine: reference book (*Mineral'ni resursy Ukrayiny: dovidnyk*). Kyiv: DNVP «Derzhavnyy heolohichnyy informatsiynyy fond Ukrayiny», 270 pp. (in Ukrainian).
- Lyko, S. and Kolesnyk, T. 2008. Economic efficiency of fertilizer application and structural reclamation on drained peat soils (*Ekonomichna efektyvnist' zastosuvannya dobryv ta strukturnykh melioratsiy na osushuvanykh torfovykh gruntakh*). *Visnyk Natsional'nyy universytet vodnoho hospodarstva ta pryrodokorystuvannya: Zbirnyk naukovykh prats'*, 4(44), pp. 51–59 (in Ukrainian).
- Melnyk, O. 2015. Geological-economic evaluation of the land South Davidkovskaya deposits of ilmenite-apatite ore in the Narodichi district of Zhytomyr region (*Heoloho-ekonomichna otsinka Pivdennoyi dilyanky Davydkiivs'koho rodovyshcha il'menit apatytovykh rud v Narodyts'komu rayoni Zhytomyr'skoyi oblasti*). Kyiv: Geoinform, 180 pp. (in Ukrainian).
- Merkushyn, I. 2014. Preliminary geological-economic evaluation Kropivnickogo deposits of titanium magnetite-ilmenite ores with apatite for the purpose of allocation of priority development area (*Poperednya heoloho-ekonomichna otsinka Kropyvnyans'koho rodovyshcha tytano-mahnyty-il'menitovykh rud z apatytom z metoyu vydilennya dilyanky pershocherhovoyi rozrobky*). Kyiv: Geoinform, 190 pp. (in Ukrainian).
- Mykhailov et al. 2007 – Mykhailov, V., Vynogradov, G. and Kurilo, M. 2007. Non-metallic minerals of Ukraine (*Nemetalichni korysni kopalyny Ukrayiny*). Kyiv: VPTS Kyiv's'kyi universytet, 503 pp. (in Ukrainian).
- Nepryakhin et al. 2015 – Nepryakhin, E., Belyaev, E., Karpova, M. and Luzhbina, I. 2015. Phosphorite component of the mineral resource base of Russia in the light of new technological opportunities (*Fosforitovaya sostavlyayushchaya MSB Rossii v svete novykh tekhnologicheskikh vozmozhnostey*). *Georesursy* 4(63), T. 1, pp. 67–74 (in Russian).
- Rudko, G. and Ozerko, V. 2016. Condition and prospects of Ukraine phosphate raw materials development (*Stan ta perspektyvy rozvytku fosfatnoyi syrovyny v Ukrayini*). *Materialy III naukovo-praktychnoyi konferentsiyi «Nadrokorystuvannya v Ukrayini: perspektyvy investuvannya»*. Truskavets, pp. 5–7 (in Ukrainian).
- Senkovskij et al. 1989 – Senkovskij, J., Glushko, V. and Senkovskij, A. 1989. Phosphorites of the Western Ukraine (*Fosfority zakhodu Ukrayiny*). Kyiv: Naukova Dumka, 182 pp. (in Ukrainian).
- Shepel, I. and Klymenko, A. 2007. The prospects for the exploration and development of mineral resources of phosphates in Ukraine (*Perspektyvy rozvytku ta osvoyennya mineral'no-syrovynnoyi bazy fosfativ v Ukrayini*) [Online] <http://www.geoproject.com.ua> [Accessed: 2019-01-18] (in Ukrainian).

- SPIU (State Institution «Soils Protection Institute of Ukraine») 2018. Operational information on the availability of mineral fertilizers for the summer-autumn field works as 26.10.2018 (*Operatyvna informatsiya shchodo zabezpechenosti mineral'nykh dobryvamy dlya provedennya litn'o-osinnikh pol'ovykh robit stanom na 26.10.2018*). [Online] <http://www.iogu.gov.ua/blog/pres-centr/novini/operatyvna-informatsiya-schodo-zabezpechenosti-mineralnymy-dobryvamy-dlya-provedennya-litno-osinnih-polovyh-robit-standom-na-26-10-2018/> [Accessed: 2019-02-1] (in Ukrainian).
- Syvvi, M. 2004. *Mineral resources of Podillya: constructive-geographical analysis and synthesis (Mineral'ni resursy Podillya: konstruktyvno-geohrafichnyy analiz i synteza)*. ISBN 966-07-0156-X. Ternopil: Pidruchnyky i posibnyky, 654 pp. (in Ukrainian).
- Ukrainets, I. 2006. Mineral resources of Vinnytsia region (*Mineral'ni resursy Vinnyts'koho rehionu*). *Produktyvnyy horyzont* 5–6, pp. 18–25 (in Ukrainian).
- Weshyckyj, W. 2004. Ukrainian resources phosphorite deposits in the aspect of sustainable development in agroecosystems (analytical review) (*Resursy ukrayins'kykh rodovysch fosforytiv v aspekti staloho rozvytku v ahroekosystemakh (analytychmyy ohlyad)*). *Materialy Mizhnarodnoyi naukovo-praktychnoyi konferentsiyi «Fosfor i kaliy u sil's'komu hospodarstvi. Problemy mikrobiolohichnoyi mobilizatsiyi»*. Chernihiv 2004, pp. 6–8 (in Ukrainian).
- VVRU 2011. National program for the development of mineral resources base of Ukraine for the period until 2030 (*Zahal'noderzhavna prohrama rozvytku mineral'no-syrovynnoyi bazy Ukrayiny na period do 2030 roku*). *Vidomosti Verkhovnoyi rady Ukrayiny* 44(457) (in Ukrainian).

**PHOSPHATES OF UKRAINE AS RAW MATERIALS
FOR THE PRODUCTION OF MINERAL FERTILIZERS AND AMELIORANTS**

Keywords

apatite ores, phosphorite ores, resources, deposits, raw materials

Abstract

The article analyzes the present state of the phosphate raw material base to meet Ukrainian chemical enterprises' needs. In Ukraine, a number of complex apatite and phosphorite deposits have been explored. Their exploitation can lead to a complete supply of Ukrainian chemical enterprises with raw materials and can partly reduce the amount of expensive imported phosphate mineral fertilizers. At present, the following deposits, where apatite is connected with other useful components, are prepared for exploitation: Stremyhorod, Fedorivka, Novopoltavka, Kropyvna and others. The advantage of the development of these deposits is the possibility to extract apatite along with the production of rare earth concentrates, ilmenite, titanomagnetite, as well as feldspars, olivine, pyroxenes, mica and others which will significantly increase the profitability of the deposits development.

The alternative to apatite-containing deposits in Ukraine can be sedimentary deposits of nodule, granular and mixed type phosphorites. Phosphorite deposits can be used mainly for the production of phosphorite and limestone flour. Considerable resources of granular phosphorites have been discovered in Volyn-Podillia and Dnieper-Donetsk which are considered to have a various agricultural effect. They are environmentally friendly ores without impurity which prevents plants from cesium, strontium and reduces nitrates in the soil. Arranging the exploration of phosphorite ores in certain parts of Volyn-Podillia basin and Dnieper-Donetsk Rift is recommended.

**FOSFORANY UKRAINY JAKO SUROWCE
DO PRODUKCJI NAWOZÓW MINERALNYCH I ŚRODKÓW POLEPSZAJĄCYCH**

Słowa kluczowe

rudy apatytowe, rudy fosforytowe, zasoby, złoża, surowce

Streszczenie

W artykule przeanalizowano obecny stan bazy surowcowej fosforanów celu zaspokojenia potrzeb ukraińskich przedsiębiorstw chemicznych. Na terenie Ukrainy odkryto kilkanaście złóż apatytu i fosforytu. Ich eksploatacja może doprowadzić do pełnego zaopatrzenia ukraińskich przedsiębiorstw chemicznych w te surowce i może częściowo zmniejszyć ilość importowanych drogich nawozów fosforowych. Obecnie do eksploatacji przygotowywane są następujące złoża, w których apatyt jest związany z innymi pożytecznymi składnikami: Stremyhorod, Fedorivka, Novopoltavka, Kropyvna i inne. Zaletą zagospodarowania tych złóż jest możliwość wydobywania apatytu wraz z produkcją koncentratów ziem rzadkich, ilmenitu, tytanomagnetytu, a także skaleni, oliwinu, piroksenów, miki i innych, co znacznie zwiększy opłacalność rozwoju złóż.

Alternatywą dla złóż zawierających apatyt na Ukrainie mogą być złoża osadowe fosforytów grubokowych, granulowanych i mieszanych. Złoża fosforytów można wykorzystać głównie do produkcji fosforytu i mąki wapiennej. Ponadto na Wołyniu Podolskim i Dnieprze-Doniecku odkryto znaczne rezerwy fosforytów ziarnistych, które mają różne zastosowanie rolnicze. Są to przyjazne dla środowiska rudy bez zanieczyszczeń, które zapobiegają tworzeniu się cezu, strontu i redukują azotany w glebie. Zaleca się dalsze poszukiwania rud fosforytów w niektórych częściach dorzecza Wołynia Podolskiego i Rowu Dniepr-Doniec.

