

Received May 31, 2018; reviewed; accepted September 2, 2018

Selective flotation of witherite from calcite using potassium chromate as a depressant

Yangshuai Qiu¹, Lingyan Zhang^{1,2}, Xuan Jiao¹, Junfang Guan^{1,2}, Ye Li^{1,2}, Yupeng Qian^{1,2}

¹ School of Resources and Environmental Engineering, Wuhan University of Technology, Wuhan 430070, China

² Hubei Key Laboratory of Mineral Resources Processing & Environment, Wuhan 430070, China

Corresponding author: zhly@whut.edu.cn (Lingyan Zhang)

Abstract: Witherite has been widely used as an industrial and environmental source of barium, with calcite being the primary associated carbonate mineral. However, few studies have been conducted to effectively concentrate witherite from barium ores. In this work, with the treatment of potassium chromate (K_2CrO_4) and sodium oleate (NaOL), witherite was selectively separated from calcite through selective flotation at different pH conditions. In addition, contact angle, Zeta potential, adsorption and X-ray photoelectron spectroscopy measurements were performed to characterize the separation mechanisms. The results demonstrated that NaOL had a strong collecting ability for both witherite and calcite; nevertheless, witherite could be effectively selected from calcite with the highest recovery at pH 9 in the presence of K_2CrO_4 . From the XPS measurements, NaOL and K_2CrO_4 were found to be primarily attached to the surfaces of witherite and calcite through chemisorption. The presence of K_2CrO_4 on the surface of calcite adversely influenced the NaOL adsorption, which could make the flotation separation efficient and successful.

Keywords: witherite, calcite, selective flotation, sodium oleate, potassium chromate

1. Introduction

Barium minerals have become the focus of scientific studies in terms of geology and beneficiation for many years, which primarily study the generation and separation of barite ores, i.e., the form of barium sulfate. Previous studies reported that barium mineralization occurs widely in the Lower Cambrian black shale (Pi et al., 2004). For a long time, barite has been the main barium mineral source in many parts of China. With the continuous improvement of exploitation technology, witherite has appeared in the shape of carbonate. More than 40 witherite deposits or witherite-barite deposits have been discovered in the Yangtze ore regions and other parts of southwestern China (Lü et al., 2004), attracting various scholars to conduct scientific investigation and experimental research on this infrequent mineral.

Witherite, also referred to as barium carbonate ($BaCO_3$), is a significant type of inorganic nonmetallic mineral that possesses favorable stability in thermodynamics with crystal modification upon heavy metal carbonates (Nagajyothi et al., 2016; Ivan et al., 2013). In general, there are three common polymorphisms of $BaCO_3$: hexagonal, orthorhombic, and cubic. Nevertheless, only the orthorhombic phase is relatively stable under ambient condition (Reto et al., 2006; Earnest et al., 1989).

As the main mineral components in rocks, carbonates are observed widely in sediments and inorganic components, among which heavy metal carbonates, especially barium carbonate, have been of considerable interest for research. Due to the close relationship between aragonite and the needle-like subunit, witherite has attracted immense attention in terms of technological process and economic values (Yu et al., 2004; Guo et al., 2012; Zhu et al., 2012), e.g., there are persistently increasing applications in industry for producing barium salts, ceramics pigment and optical glass (Lv et al., 2007; Thongtem et al., 2010). However, the high-cost and energy-inefficient preparation processes on the basis

of barite have led to the application of witherite as stock materials (Hu et al., 2014; Gao et al., 2011; Zhang et al., 2011).

In addition, BaCO_3 is widely utilized in synthesizing barium ferrites and ferroelectric materials as a precursor in a relatively low-cost and high-efficiency way (Sreedhar et al., 2012; Jiao et al., 2010; Alavi et al., 2008). In recent years, various chemical and physical methods have been used to synthesize barium nanoparticles using witherite as raw materials, such as solid-state decomposition, microemulsion-based method (Li et al., 2006), reversed micelles (Karagiozov et al., 2005), and self-organized formation methods (Xie et al., 2005). In general, there is a growing demand for witherite in the modern industry. Therefore, the beneficiation and purification of witherite from other gangues are of great significance.

With a relatively narrow distribution in the whole world, a rare effective method has been found to concentrate witherite in barium ore. Calcite is one of the main gangue minerals in witherite ore (Gao et al., 2017; Yang et al., 2008; Barkhordari et al., 2009). The surface chemical properties of witherite and calcite are similar due to that fact that they both belong to carbonate minerals. NaOL has been widely used in the flotation of semisoluble salt-type minerals, such as scheelite, calcite, fluorite, barite, and celestite (Martinez et al., 2003, Li and Gao, 2018 and 2017; Gao et al., 2018a), showing a pronounced collecting power but a poor selectivity of the valuable minerals. Therefore, efficient calcite depressants are supposed to be utilized for improving the selectivity in the separation of witherite and calcite by modifying the mineral surface characteristics. Depressants for calcite in previously published papers are mainly focused on water glass (Gao et al., 2016a; Wang et al., 2016; Haisheng et al., 2017), phosphates (Gao et al., 2018; Yongxin and Changgen, 1983) and some hydrophilic colloids (Liu et al., 2016; Ozcan and Bulutcu, 1993; Shi et al., 2014; Tian et al., 2017). These depressants are reported to improve the flotation selectivity with some effect, but depress witherite to a large extent at the same time. Therefore, there is a considerable demand for developing more selective depressants with high performance for the separation of witherite from calcite. Potassium chromate has been widely used as a depressant for galena in flotation. Meanwhile, potassium chromate has depressing effects on calcite, pyrite, etc. (Huangpu, 1985; Zhang et al., 2008). In a previous work, potassium chromate was used as a depressant for calcite for the separation of fluorite and calcite. Fluorite and calcite could be separated effectively by flotation when the potassium chromate concentration was $9 \times 10^{-5} \text{ mol/L}$ by using NaOL as the collector (Yu, 2015).

The purpose of this study is to investigate the separation of witherite from calcite using potassium chromate as a depressant. Consequently, batch flotation tests of single minerals and artificial mixtures composed of witherite and calcite single minerals were performed, with sodium oleate (NaOL) and potassium chromate (K_2CrO_4) being the collector and depressant, respectively. In addition, ultraviolet spectrophotometry, X-ray photoelectron spectroscopy (XPS), Zeta potential and contact angle measurements were performed to explain the mechanism.

2. Materials and methods

2.1. Materials

Witherite single mineral sample was obtained from Chengkou county in Sichuan province, China. High grade minerals were crushed to -2 mm by roll crushing milling and were ground in a conical ball mill with steel balls as the media under wet condition. Finally, -0.100 mm +0.074 mm particle size fraction was collected. According to the Chinese national standard (GB/T 1614-2011, Barium Carbonate for Industrial Use; a Chinese national standard had been made to define the determination method of BaCO_3 and impurities content in industrial barium carbonate), the barium carbonate content of witherite single mineral was analyzed to be approximately 92%. X-ray fluorescence (XRF) analysis indicated 72.44 wt.% BaO, 0.94 wt.% CaO, 2.78 wt.% SiO_2 , and 0.78 wt.% MgO. The X-ray diffraction pattern of witherite single mineral is shown in Fig. 1a. The main minerals in the witherite single mineral were witherite and barytocalcite according to the X-ray diffraction pattern. The contents of these two minerals could be calculated according to the contents of BaO and CaO analyzed by XRF. The witherite single mineral contained approximately 91 wt.% of witherite, 5 wt.% of barytocalcite, and 4 wt.% of other gangue minerals.

The calcite single mineral sample was obtained from Wuling county in Chongqing city, China. It was also handled via the same method applied for witherite. X-ray fluorescence (XRF) analysis indicated 55.16 wt.% CaO, 0.65 wt.% SiO₂, and 0.24 wt.% Al₂O₃. Fig. 1b displays the X-ray diffraction pattern of calcite. Combining with XRF analysis, the content of calcite in the sample was greater than 98.50 wt%.




Fig. 1. XRD patterns of single minerals: (a) witherite; (b) calcite

Sodium oleate (NaOL) and potassium chromate (K₂CrO₄) were used as the collector and depressant, respectively, and both were purchased from Sinopharm Chemical Reagent Co., Ltd. Hydrochloric acid (HCl) or sodium hydroxide (NaOH) solutions were used to adjust the pH value of the slurry, while deionized water was applied for all experiments. All reagents were of analytical grade and used without further purification.

2.2. X-ray diffraction analysis

The mineral composition of single mineral samples was determined by using a D8 Advance model X-ray powder diffractometer (Bruker Corporation, Stuttgart, Germany), with Cu K α radiation ($\lambda=1.5406$ Å). The data of the samples were collected with 2θ values ranging from 5° to 70° at a scan speed of 1°/min.

2.3. X-ray photoelectron spectroscopy (XPS)

X-ray photoelectron spectroscopy (XPS) of the samples was performed on a Thermo Electron Corporation (Waltham, MA, USA) VG Multilab 2000 with a monochromatic Al X-ray source operating at 300 W. The survey was scanned from 0 to 1100 eV with a pass energy of 100 eV and steps of 1.0 eV. Only 1 sweep was carried out. 1.0 g of single mineral samples with a fraction of -74 μm was added into 30 mL of deionized water. Then, the slurries were conditioned using the same procedure as the flotation tests with and without desired reagents. After stirring for 10 min and washing twice with deionized water, the slurries were filtered and dried in a vacuum desiccator controlled at a temperature below 30°C for 24 h.

2.4. Ultraviolet spectrophotometry

The adsorption amount was recorded on an A360 ultraviolet spectrophotometer (AOE Instruments (Shanghai) Co., Ltd, Shanghai, China). 2.5 g of mineral sample was mixed with 25 mL of deionized water in the flotation cell for 1 min. Then, the desired concentration of reagents was added to the pulp in order and conditioned for 2 min for each reagent at room temperature (25 °C). The solid phase was separated from the solution using a H2050R-1 high-speed centrifuge (CENCE Instruments Co., Ltd., Hunan, China). Next, the supernatant of the solution was used to measure the residual NaOL concentration using the spectrophotometer with the wavelength set at 192 nm, which is the characteristic adsorption band of NaOL (Zheng et al., 2017).

2.5. Zeta potential measurements

The tested sample particles were ground to $-2.0\ \mu\text{m}$ in an agate mortar, and 20 mg of the sample was added into 100 mL of deionized water. The Zeta potentials were measured using a Malvern Zetasizer Nano ZS90 (Malvern Instruments, Malvern, UK). All measurements were conducted in a 0.1 mol/L NaCl background electrolyte solution. The pH value of the suspension solution was adjusted by HCl or NaOH solutions. The measurements were performed at 25 °C.

2.6. Contact angle measurements

The contact angles of single minerals treated or untreated by the reagent to assess the wettability were measured on a GBX MiniLab ILMS (GBX Scientific Instruments, Romans, France), whose operating principle is the Washburn technique (Qiu et al., 2016; Chibowski et al., 2002; Chau, 2009). 10 g of mineral samples were added into 200 mL of deionized water, and then the slurries were conditioned using the same procedure as the flotation tests with and without desired reagents. After stirring for 10 min and washing twice with deionized water, the slurries were then filtered, and dried in a vacuum desiccator controlled at a temperature below 30°C. Each value reported was the average of three separate determinations.

2.7. Batch flotation tests

The flotation tests for single minerals or the artificial mixture composed of 60 wt% witherite and 40 wt% calcite were conducted in an XFG-35 laboratory mechanical flotation cell with a volume of nearly 35 mL (Gao et al., 2016a and 2016b; Gao et al., 2018a). First, 2.5 g of mixture was added along with 25 mL of deionized water into the flotation cell for 1 min at an impeller speed of 1800 rpm. Second, HCl or NaOH was added into the pulp to adjust the solution pH. Next, K_2CrO_4 and NaOL were added to the pulp in order, with a condition time of 2 min for each reagent. The total flotation time was 3 min, with the concentrates being collected by manual scraping. The concentrates as well as the unfloated products remaining in the cell were collected, dried and weighed to calculate the flotation recoveries. The element contents of Ba and Ga in the concentrate were measured by XRF. Contents of witherite and calcite in the artificial mixture flotation concentrate were calculated according to the element contents of Ba and Ga. The recoveries of witherite and calcite were calculated according to their contents in the concentrate.

3. Results and discussion

3.1. Wettability of witherite and calcite

To assess the wettability of witherite and calcite, the contact angles of single minerals treated or untreated by the collector and depressant were measured under the condition of different pH values. The effect of K_2CrO_4 and NaOL on the wettability of witherite and calcite powder is shown in Fig. 2.




Fig. 2. Powder contact angle of single minerals treated or untreated by the collector and depressant: (a) witherite; (b) calcite

Under neutral condition, the initial contact angle of witherite powder was 22° while the initial contact angle of calcite powder was 75° , which agreed with the result of Przemyslaw B. et al. (2017). When treated by NaOL, the contact angles of witherite and calcite were increased from 22° to 118° and from 75° to 93° , respectively, implying that witherite and calcite became extremely hydrophobic. While K_2CrO_4 was attached on the surface, the contact angle of calcite was decreased fiercely to 49° . Compared with calcite, the contact angle of witherite was decreased in a relatively slight extent, indicating that K_2CrO_4 had little effect on depressing witherite.

3.2. Batch flotation of single mineral and artificial mixture

To investigate the collecting and depressing effects of K_2CrO_4 and NaOL on witherite and calcite, batch tests of single minerals and artificial mixture were conducted, and the results are shown in Fig. 3.




Fig. 3. Recovery of flotation on single mineral and artificial mixture: (a) single mineral; (b) artificial mixture

The recoveries of both witherite and calcite were at a high level when 25 mg/L NaOL was used as the collector within the pH range of 7 to 12, reaching the maximum at pH 9. Once 15 mg/L K_2CrO_4 was added into the pulp as the depressant, calcite showed a poor floatability while witherite was quite hydrophobic, with the optimal pH value being still 9, which agreed with the contact angle tests. The recoveries of the artificial mixture were identical to single mineral flotation, e.g., the recoveries of witherite and calcite were both at a high level when NaOL was used as the collector in the pH range from 7 to 12. However, after the addition of K_2CrO_4 , the difference in the recovery of witherite and calcite was observed, with the greatest difference being found at pH 9, indicating the best separation efficiency under this condition. It should be noted that NaOL had a decent collecting ability for both witherite and calcite. In addition, pH and K_2CrO_4 played an important role in the separation between witherite and calcite.

3.3. Zeta potential measurement

The Zeta potentials of witherite and calcite before and after being treated by K_2CrO_4 or NaOL or K_2CrO_4 +NaOL are shown in Fig. 4.

From the electrokinetic phenomenon of witherite and calcite suspensions shown in Fig. 4, the minerals were negatively charged within pH 7 ~ 12. Once treated by K_2CrO_4 or NaOL or K_2CrO_4 +NaOL, the zeta potentials of witherite and calcite were shifted down, becoming more negatively charged, probably due to the adsorption of K_2CrO_4 and NaOL on the mineral surfaces.

Specifically, Fig. 4(a) illuminated that the decrease in the zeta potentials of witherite with the intercalation of NaOL was greater than those treated by K_2CrO_4 , reflecting the better adsorption of NaOL on witherite *vs.* K_2CrO_4 , opposite to that of calcite shown in Fig. 4(b). The zeta potential curve of "witherite + K_2CrO_4 + NaOL" was very close to that of "witherite + NaOL", indicating that preadsorbed K_2CrO_4 slightly influenced the adsorption of NaOL on witherite. The zeta potential curve of calcite treated by " K_2CrO_4 + NaOL" was very close to that of "calcite + K_2CrO_4 ", reflecting better adsorption of K_2CrO_4 on calcite *vs.* NaOL. Moreover, the adsorption efficiency of witherite was the strongest at pH of

9 and 10, while that of calcite became stronger gradually with increasing pH, consistent with the results of the flotation tests.




Fig. 4. Zeta potentials of witherite and calcite before and after being treated by K_2CrO_4 or NaOL or $K_2CrO_4 + NaOL$. (a) witherite; (b) calcite

3.4. Adsorption measurement of the collector

The adsorption difference of the collector on the different mineral surfaces is the premise for implementing mineral separation via froth flotation. This difference could be intuitively reflected by the apparent adsorption amount. Table. 1 shows the adsorption amounts of NaOL on witherite and calcite analyzed using a UV spectrophotometer.

Table 1. The adsorbed rates of sodium oleate attached on the surface

Reagent regime	Abs	Residual rate/%	Adsorbed rate/%
NaOL	0.361	100.00	0
$BaCO_3+NaOL$	0.088	23.55	76.45
$BaCO_3+K_2CrO_4+ NaOL$	0.112	31.02	68.98
$CaCO_3+ NaOL$	0.147	40.72	59.28
$CaCO_3+K_2CrO_4+ NaOL$	0.309	85.60	14.40

NaOL showed an out-bound adsorption on both witherite and calcite, in accordance with the high recovery in single mineral flotation. It should be noted that the adsorption rate on witherite was higher than that on calcite, indicating a better collecting ability for witherite. However, an almost 45% descend of NaOL adsorption was observed on the calcite surface in the presence of K_2CrO_4 . In contrast, only a slight decrease of approximately 7.47% for witherite was found. To sum up, the attachment of K_2CrO_4 on calcite surface had a beneficial effect on the depression of NaOL adsorption, making the flotation of calcite more moderate to separate from witherite.

3.5. XPS analysis

As a surface-sensitive technique, XPS has been widely applied in the analysis of mineral surface properties (Chen et al., 2014; Peng et al., 2012; Wang et al., 2014; Zhao et al., 2015). Table.2 summarizes the atomic compositions of witherite and calcite interfaces before and after K_2CrO_4 and NaOL treatments. With the addition of K_2CrO_4 and NaOL, the atomic concentrations of C, O, and Cr were increased but that of Ca was decreased on the surface of calcite, indicating an obvious adsorption of K_2CrO_4 but a small adsorption of NaOL. For witherite, contrary to the result of calcite, there was a noticeable augment in the atomic concentration of C and a small increase in the atomic concentration of Cr, along with a decrease in the concentrations of Ba and O, which identify the high adsorption of NaOL and the small amount of adsorbed K_2CrO_4 .

The XPS high-resolution spectra of C 1s, Ca 2p or Ba 2p on witherite and calcite with and without the treatments of K_2CrO_4 and NaOL are shown in Fig. 5 and Fig. 6, respectively. Fig. 5 indicated that the binding energies of C 1s peaks in calcite were located at 288.30 and 283.92 mV, which were shifted to other values with the addition of K_2CrO_4 and NaOL, implying that there was a weak chemisorption of NaOL on the surface of calcite. The binding energies of Ca 2p appeared at approximately 345.78 and 349.28 mV and were shifted to smaller values at approximately 345.39 and 349.15 mV after the treatments of K_2CrO_4 and NaOL, implying that K_2CrO_4 could chemisorb with Ca atoms on the surface of calcite. These phenomena illuminated that the addition of K_2CrO_4 and NaOL changed the chemical circumstance of Ca atoms on the surface but seldom changed that of superficial C.

Table 2. Atomic concentration of elements on the mineral interfaces by XPS

Samples	Atomic concentration of elements/%				
	Ca	Ba	C	O	Cr
Calcite	17.41	/	24.92	57.67	0
Calcite+ K_2CrO_4 +NaOL	11.93	/	26.79	58.96	2.37
Δ	-5.48	/	1.87	1.29	2.37
Witherite	/	17.58	28.45	53.97	0
Witherite+ K_2CrO_4 +NaOL	/	9.07	47.78	42.71	0.44
Δ	/	-8.51	19.33	-11.26	0.44

“Δ”- The variation of atomic concentration




Fig. 5. XPS high-resolution spectra of C 1s, Ca 2p on calcite with and without the treatment of K_2CrO_4 and NaOL: (a) C 1s; (b) Ca 2p




Fig. 6. XPS high-resolution spectra of C 1s, Ba 3d on witherite with and without the treatment of K_2CrO_4 and NaOL: (a) C 1s; (b) Ba 3d

Fig. 6 shows that the binding energies of C 1s and Ba 3d of witherite experienced a notable change before and after the addition of K_2CrO_4 and NaOL. Specifically, the binding energy of C 1s on witherite treated by K_2CrO_4 and NaOL was located at 289.24 and 284.78 mV, significantly different from the binding energies of 288.66 and 284.28 mV without the treatments, which can be attributed to the carboxyl or carbonyl groups of sodium oleate (Jin et al., 2016; Takahagi et al., 1984). The findings could reveal that sodium oleate was chemisorbed on the surface of witherite effectively. In addition, the great changes in binding energy of Ba 3d from 794.48 and 778.98 mV to 794.08 and 778.39 mV indicated the chemical interaction between the anionic molecules and superficial barium atoms. These performances clarified that sodium oleate had a high negative charge and could combine with the barium atoms effortlessly with a fantastic collectability on witherite in the absence or presence of potassium chromate.

4. Conclusions

Witherite and calcite showed a slight difference in the flotation behaviors when NaOL was used as the collector during batch flotation experiments of single minerals, with a slightly higher recovery being observed for witherite. The flotation experiments for artificial mixtures showed that the difference in the recovery of witherite and calcite became more conspicuous in the presence of K_2CrO_4 , reaching the maximum at pH 9. These findings were in agreement with the results of contact angle measurements.

Witherite showed a better adsorption capability for NaOL *vs.* K_2CrO_4 , contrary to the result of calcite on account of the zeta potential measurement. In addition, the addition of K_2CrO_4 had a good effect on the depression of NaOL adsorption on calcite surface, but poorly influenced the adsorption on witherite surface.

XPS measurements confirmed that NaOL had a strong chemical interaction with witherite in the presence of K_2CrO_4 but had weak and even absent adsorption on the calcite surface under the same circumstance. In addition, NaOL and K_2CrO_4 were found to be adsorbed on the surfaces of witherite and calcite via chemical interaction with barium or calcium atoms. With the treatments of K_2CrO_4 and NaOL, witherite can be separated from calcite effectively by the means of forth flotation.

Acknowledgments

The financial support for this work provided by the Fundamental Research Funds for the Central Universities (WUT: 2017zy073) is gratefully acknowledged, and technical support from the Center for Analysis of Wuhan University of Technology. The first author thanks the Excellence Scholarship provided by Wuhan University of Technology.

References

- ALAVI A.M., MORSALI A., 2008. *Syntheses of $BaCO_3$ nanostructures by ultrasonic method.* Ultrason. Sonochem., 15, 833-838.
- BARKHORDARI H.R., JORJANI E., ESLAMI A., Noaparast M., 2009. *Occurrence mechanism of silicate and aluminosilicate minerals in Sarcheshmeh copper flotation concentrate.* Int. J. Min. Met. Mater., 16, 494-499.
- CHAU T.T., 2009. *A review of techniques for measurement of contact angles and their applicability on mineral surfaces.* Minerals Engineering, 22, 213-219.
- CHIBOWSKI E., PEREA-CARPIO R., 2002. *Problems of contact angle and solid surface free energy determination.* Adv. Colloid Interface Sci., 98, 245-264.
- CHEN X.M., PENG Y.J., BRADSHAW D., 2014. *The effect of particle breakage mechanisms during regrinding on the subsequent cleaner flotation.* Miner. Eng., 66-68, 157-164.
- DADKHAH M., SALAVATI-NIASARI M., DAVAR F., 2013. *A new inorganic framework in the synthesis of barium carbonate nanoparticles via convenient solid state decomposition route.* Adv. Powder Technol., 24, 14-20.
- EARNEST C.M., 1989. *Calorimetric heat of transition assignments by microcomputer-based differential thermal analysis: Part II. The γ - β (orthorhombic to hexagonal) transition of barium carbonate,* Thermochim. Acta, 137, 365-371.
- GAO W., ZHOU B., MA X.Y., LIU Y., WANG Z.C., ZHU Y.C., 2011. *Preparation and characterization of $BaSO_4$ /poly (ethylene terephthalate) nanocomposites.* Colloids Surf., A: Physicochem. Eng. Aspects, 385, 181-187.

- GAO J.B., YANG R.D., CHEN J., ZHENG L.L., CHENG W., WEI H.R., 2017. *Multiple proxies indicating methane seepage as the origin of Devonian large barite deposit in Zhenning-Ziyun, Guizhou, SW China*. *Ore Geol. Rev.*, 80, 18-26.
- GAO, Z.Y., XIE, L., CUI, X., HU, Y.H., SUN, W., ZENG, H.B., 2018a. *Probing Anisotropic Surface Properties and Surface Forces of Fluorite Crystals*. *Langmuir*, 2018, 34: 2511-2521.
- GAO, Y., GAO, Z., SUN, W., YIN, Z., WANG, J., HU, Y., 2018b. *Adsorption of a novel reagent scheme on scheelite and calcite causing an effective flotation separation*. *J. Colloid Interface Sci.* 512, 39-46.
- GAO, Y.S., GAO, Z.Y., SUN, W., HU, Y.H., 2016a. *Selective flotation of scheelite from calcite: A novel reagent scheme*, *International Journal of Mineral Processing*, 154,10-15.
- GAO, Z.Y., GAO, Y.S., ZHU, Y.Y., HU, Y.H., SUN, W., 2016b. *Selective flotation of calcite from fluorite: a novel reagent schedule*. *Minerals*, 6 (4), 114.
- GUO X.H., MENG F.L., QU X.N., WANG M.J., MAO C.C., ZHANG J., WANG W.V., YU S.H., 2012. *Mineralization of unique barium carbonate crystal superstructures controlled by a liquid crystalline phase polymer*. *Cryst. Eng. Comm.*, 14, 3213-3219.
- HAN H.S., HU Y.H., SUN W., LI X.D., CAO C.G., LIU R.Q., YUE T., MENG X.S., GUO Y.Z., WANG J.J., GAO Z.Y., CHEN P., HUANG W.S., LIU J., XIE J.W., CHEN Y.L., 2017. *Fatty acid flotation versus BHA flotation of tungsten minerals and their performance in flotation practice*. *Int. J. Miner. Process.* 159, 22-29.
- HU L.N., WANG G.X., CAO R., YANG C., CHEN X., 2014. *Fabrication and surface properties of hydrophobic barium sulfate aggregates based on sodium cocoate modification*, *Appl. Surf. Sci.*, 315, 184-189.
- HUANGPU S.Y., 1985. *The practice of improving the quality of molybdenum concentrate by using Potassium chromate*. *China Molybdenum Industry*, 01, 31-41.
- IVAN S., EGON M., 2013. *Homogeneous Precipitation by Enzyme-Catalyzed Reactions 2. Strontium and Barium Carbonates*. *Chem. Mater.*, 15, 1322-1326.
- JIAO J.Q., LIU X., GAO W., WANG C.W., FENG H.J., ZHAO X.L., CHEN L.P., 2010. *Two-step synthesis of witherite and tuning of morphology*. *Mater. Res. Bull.*, 45, 181-185.
- JIN J.X., GAO H.M., REN Z.J., CHEN Z.J., 2016. *The Flotation of Kyanite and Sillimanite with Sodium Oleate as the Collector*. *Minerals*, 6, 90.
- KARAGIOZOV C., MOMCHILOVA D., 2005. *Synthesis of nano-sized particles from metal carbonates by the method of reversed mycelles*. *Chem. Eng. Process.*, 44, 115.
- LÜ Z.C., LIU C.Q., LIU J.J., WU F.C., 2004. *The bio-barite in witherite deposits from Southern Qinling and its significance*. *Prog. Nat. Sci.*, 14, 889-896.
- LV S., LI P., SHENG J., SUN W.D., 2007. *Synthesis of single-crystalline BaCO₃ nanostructures with different morphologies via a simple PVP-assisted method*. *Mater. Lett.*, 61, 4250-4254.
- LI, C., GAO Z., 2017. *Tune surface physicochemical property of fluorite particles by regulating the exposure degree of crystal surfaces*. *Miner Eng.* 128, 123-132.
- LI, C., GAO Z., 2017. *Effect of grinding media on the surface property and flotation behavior of scheelite particles*. *Powder Technol.* 322, 386-392.
- LI L.L., CHU Y., LIU Y., DONG L.H., HUO L., YANG F.Y., 2006. *Microemulsion-based synthesis of BaCO₃ nanobelts and nanorods*. *Mater. Lett.*, 60, 2138-2142.
- LIU, C., FENG, Q., GUOFAN, ZHANG, 2016. *Effect of depressants in the selective flotation of scheelite and calcite using oxidized paraffin soap as collector*. *Int. J. Miner. Process.* 157, 210-215.
- MARTINEZ A., URIBE A., CARRILLO F.R., CORENO J., ORTIZ J.C., 2003. *Study of celestite flotation efficiency using sodium dodecyl sulfonate collector: factorial experiment and statistical analysis of data*. *Int. J. Miner. Process.* 70, 83-97.
- NAGAJYOTHI P.C., PANDURANGAN M., SREEKANTHC T.V.M., SHIM J., 2016. *In vitro anticancer potential of BaCO₃ nanoparticles synthesized via green route*. *J. Photochem. Photobiol.*, B, 156, 29-34.
- OZCAN, O., BULUTCU, A.N., 1993. *Electrokinetic, infrared and flotation studies of scheelite and calcite with oxine, alkyl oxine, oleoyl sarcosine and quebracho*. *Int. J. Miner. Process.* 39, 275-290.
- PI D.H., JIANG S.Y., LUO L., YANG J.H., LING H.F., 2004. *Depositional environments for stratiform witherite deposits in the Lower Cambrian black shale sequence of the Yangtze Platform, southern Qinling region, SW China: Evidence from redox-sensitive trace element geochemistry*. *Palaeogeogr. Palaeoclimatol. Palaeoecol.* 398, p.125.
- PENG Y.J., WANG B., GERSON A., 2012. *The effect of electrochemical potential on the activation of pyrite by copper and lead ions during grinding*. *Int. J. Miner. Process.*, 102-103, 141-149.

- PRZEMYSŁAW B. K., CANDOGAN A., MAHMUT E., MIKOLAJ J. J., OKTAY S., JAN D., 2017. *Water Contact Angle on Corresponding Surfaces of Freshly Fractured Fluorite, Calcite and Mica*. Physicochem. Probl. Miner. Process., 53, 192-201.
- QIU Y.S., YU Y.F., ZHANG L.Y., QIAN Y.P.; OUYANG Z.J., 2016. *An Investigation of Reverse Flotation Separation of Sericite from Graphite by Using a Surfactant: MF*. Minerals, 6, 57.
- RETO S., MAREK M., SOTIRIS E.P., ALFONS B., 2006. *Unprecedented formation of metastable monoclinic BaCO₃ nanoparticle*. Thermochemica Acta, 445, 23-26.
- SHI, Q., FENG, Q., ZHANG, G., DENG, H., 2014. *A novel method to improve depressants actions on calcite flotation*. Miner. Eng. 55, 186-189.
- SREEDHAR B., VANI S.C., DEVI K.D., RAO B.M.V., RAMBABU C., 2012. *Shape Controlled Synthesis of Barium Carbonate Microclusters and Nanocrystallites using Natural Polysachharide-Gum Acacia*, Am. J. Mater. Sci., 2, 5-13.
- TAKAHAGI T., ISHITANI A., 1984. *XPS studies by use of the digital difference spectrum technique of functional groups on the surface of carbon fiber*. Carbon, 22, 43-46.
- TIAN, M., GAO, Z., HAN, H., SUN, W., HU, Y., 2017. *Improved flotation separation of cassiterite from calcite using a mixture of lead (II) ion / benzohydroxamic acid as collector and carboxymethyl cellulose as depressant*. Miner Eng, 113, 68-70.
- THONGTEM T., TIPCOMPORN., PHURUANGRAT A., THONGTEM S., 2010. *Characterization of SrCO₃ and BaCO₃ nanoparticles synthesized by sonochemical method*. Mater. Lett., 64, 510-512.
- WANG J., GAO Z., GAO Y., HU Y., SUN W., 2016. *Flotation separation of scheelite from calcite using mixed cationic/anionic collectors*. Miner Eng, 98, 261-263.
- WANG L., SUN W., HU Y.H., XU L.H., 2014. *Adsorption mechanism of mixed anionic/cationic collectors in Muscovite-Quartz flotation system*. Miner. Eng., 64, 44-50.
- XIE A.J., SHEN Y.H., ZHANG C.Y., YUAN Z.W., ZHU X.M., YANG Y.M., 2005. *Crystal growth of calcium carbonate with various morphologies in different amino acid systems*. J. Cryst. Growth, 285, 436-443.
- YANG R.D., WEI H.R., BAO M., WANG W., WANG Q., ZHANG X.D., LIU L., 2008. *Discovery of hydrothermal venting community at the base of Cambrian barite in Guizhou Province, Western China: implication for the Cambrian biological explosion*. Prog. Nat. Sci., 18, 65-69.
- YONGXIN, L., CHANGGEN, L., 1983. *Selective flotation of scheelite from calcium minerals with sodium oleate as a collector and phosphates as modifiers. I. selective flotation of scheelite*. Int. J. Miner. Process. 10, 205-218.
- YU S.H., CÖLFEN H., XU A.W., DONG W.F., 2004. *Complex Spherical BaCO₃ Superstructures Self-Assembled by a Facile Mineralization Process under Control of Simple Polyelectrolytes*. Cryst. Growth Des., 4, 33-37.
- YU F.T., 2015. *Study on Flotation Behavior between Fluorite, Barite and Calcite in Wuling Mountain*, M.A. Thesis, Wuhan University of Technology, Wuhan, China.
- ZHU W.J.; CAI C.H.; LIN J.P.; WANG L.Q.; CHEN L.L.; ZHUANG Z.L., 2012. *Polymer micelle-directed growth of BaCO₃ spiral nanobelts*. Chem. Commun. 48, 8544-8546.
- ZHANG M., ZHANG B., LI X.H., YIN Z.L., GUO X.Y., 2011. *Synthesis and surface properties of submicron barium sulfate particles*. Appl. Surf. Sci., 258, 24-29.
- ZHANG J.S., QUE X.L., (Ed.), 2008. *Mineral Processing Reagents*, Metallurgy Industry Press, Beijing, Chap. 12
- ZHAO G., WANG S., ZHONG H., 2015. *Study on the Activation of Scheelite and Wolframite by Lead Nitrate*. Minerals, 5, 247-258.
- ZHENG R.J., REN Z.J., GAO H.M., QIAN Y.P., 2017. *Flotation Behavior of Different Colored Fluorites Using Sodium Oleate as a Collector*. Minerals, 7, 159.