

Kwiryn Wojsyk, Maksym Grzywiński, Iwona Pokorska

WELDING RESIDUAL STRESSES IN STEEL STRUCTURES

The purpose of the paper is to analyse the welding residual stresses in various welding structures. The literature on residual stresses is broad (see [1-26], for instance). In this paper the plug weld and circular path weld are discussed. Plug welded element made of low carbon steel is shown in Figure 1. The distribution of residual stresses is shown in Figure 2.

In the weld and adjacent areas tensile stresses equal to the yield stress of the material are observed both in radial and tangential directions.

In areas away from the weld, radial stresses σ_r are tensile and tangential stresses σ_θ are compressive. Both stresses decreased as the distance from the weld increased.



Fig. 1. Plug welded element




Fig. 2. Distribution of residual stresses in a plug weld

Patch weld which are used in repair jobs is shown in Figure 3. Consider a circular plate welded into a large plate with a circular hole. Since shrinkage of the inner plate is restrained by the surrounding outer plate, high residual stresses are produced. The typical distribution of residual stresses in circular patch welds is shown in Figure 3. The radial stresses σ_r and tangential stresses σ_θ are presented along the diameter. High tensile residual stresses exist in the weld area. The maximum of tangential stress is higher than the maximum radial stress. In the inner plate, radial and tangential stresses are tensile and approximately equal.




Fig. 3. Residual stresses in a circular patch weld

Residual stresses in a path weld are produced primarily by shrinkage of the weld metal in the direction parallel to the weld or in the circumferential direction and shrinkage of the weld metal in the direction perpendicular to the weld or in the radial direction.

Civil structures are often fabricated by welding. The typical distribution of residual stresses is shown in Figure 4.

First one shows residual stresses in a welded T-shape. High tensile residual stresses parallel to the axis are observed in areas near the weld in sections away from the end of the column. Stresses in the flange are tensile near the weld and compressive away from the weld. The tensile stresses near the upper edge of the weld are due to the longitudinal bending distortion caused by longitudinal shrinkage. Angular distortion is also observed.

The typical distribution of residual stress in an H-shape and a box shape are shown in Figure 4.




Fig. 4. Residual stresses in welded shapes




Fig. 5. Residual stresses in a cylindrical tank

The residual stresses shown are parallel to the axis. These are tensile in areas near the welds and compressive in areas away from the weld. In Figure 5 residual stresses in cylindrical tank are presented.

References

- [1] Alpsten G.A., Tall L., Residual stresses in heavy welded shapes, *Welding Journal* 1970, 39(3), Research Supplement, 93-105.
- [2] Bentley K.P., Greenwood J.A., McKnowlson P., Bakes R.G., Temperature distributions in spot welds, *Brit. Weld. Journal* 1963, 613-619.
- [3] Brust F.W., Kanninen M.F., Analysis of residual stresses in girth welded type 304-stainless pipes, *ASME Journal of Materials in Energy Systems* 1981, 3(3).
- [4] Eager T.W., Tsai N.S., Temperature fields produced by traveling distributed heat sources, *Welding Journal* 1983, 62(12), 346-355.
- [5] Hess W.F., Merrill L.L., Nippes E.F. Jr., Bunk A.P., The measurement of cooling rates associated with arc welding and their application to the selection of optimum welding conditions, *Welding Journal* 1943, 22 (9), Research Supplement, 377-422.
- [6] Jeong S.K., Cho H.S., An analytical solution to predict the transient temperature distribution in fillet arc welds, *Welding Journal* 1997, 76(6), 223-232.
- [7] Jhaveri Pravin Moffatt W.G., Adams C.M. Jr., The effect of plate thickness and radiation on heat flow in welding and cutting, *Welding Journal* 1962, 41(1), Research Supplement, 12-16.
- [8] Kasuya T., Yurioka N., Prediction of welding thermal history by a comprehensive solution, *Welding Journal* 1993, 72(3), 107-115.
- [9] Kawai T., A study on residual stresses and distortion in welded structures, *Journal of the Japan Welding Society* 1964, 33(3), 314.
- [10] Kawai T., Yoshimura N., A study on residual stresses and distortion in welded structures (Part 2), *Journal of the Japan Welding Society* 1965, 34(2), 214, and Part 3 1965, 34 (12), 215.
- [11] Murray J.D., Welding of high yield point steels, *Welding and Metal Fabrication* 1966, 8.
- [12] Nagaraja Rao N.R., Esatuar F.R., Tall L., Residual stresses in welded shapes, *Welding Journal* 1964, 43(7), Research Supplement, 295-306.
- [13] Prokhorov N.N., Samotokhin S.S., Effect of artificial flowing off of Heat on processes of developing internal stresses and strain in welding, *Avt. Proiz.* 1977, 5, 63-69.
- [14] Rabkin D.M., Temperature distribution through the weld pool in the automatic welding of aluminium, *British Welding Journal* 1959, 6(8), 132-137.
- [15] Rosenthal D., Cambridge M., The theory of moving source of heat and its application to metal treatments, *Trans. ASME* 1946, 68(11), 849-866.
- [16] Rosenthal D., The theory of moving sources of heat and its application to metal treatments, *ASME Trans.* 1946, 849-866.
- [17] Rykalin N.N., *Berechnung der Wärmevorgänge beim Schweißen*, Verlag Technik, Berlin 1957, 68-69.
- [18] Rykalin N.N., Calculation of heat processes in welding, Lecture the presented before the American Welding Society 1961, April.
- [19] Rykalin N.N., Calculations of thermal processes in welding, Mashgiz, Moscow 1951.
- [20] Służalec A., *Theory of thermomechanical processes in welding*, Springer, 2005.
- [21] Sudnik W., Research into fusion welding technologies based on physical-mathematical models, *Welding & Cutting* 1991, 43, E216-E217.
- [22] Vogel L.E., Lyens J.V., Pumphrey W.I., Temperature and hardness distribution in welded Al-4% Cu alloy sheet, *Brit. Weld. Journal* 1954, 252-259, June.

-
- [23] Wayman S.M., Stout R.D., A study of factors effecting the strength and ductility of weld metal, *Welding Journal* 1958, 5.
- [24] Wilson W.M., Hao C.C., Residual stresses in welded structures, *The Welding Journal* 1974, 26(5), Research Supplement, 295-320.
- [25] Yang Y.P., Brust F.W., Welding-induced distortion control techniques in heavy industries, Symposium on Weld Residual Stresses and Fracture 2000, ASME Pressure Vessels and Piping Conference, Seattle, WA, USA, July 23-27 2000.
- [26] Yoshida T., Abe T., Onoue H., Residual stresses in circular-patch-welds, *Journal of the Society of Naval Architects of Japan* 1959, 105.

Abstract

The purpose of the paper is to analyze the welding residual stresses in various kinds of welding structures. The paper has a review character.

Streszczenie

Celem pracy jest analiza naprężeń spawalniczych w różnego rodzaju konstrukcjach spawanych. Praca ma charakter przeglądowy.